

## PTFE0S - Teflon®

# NON-SHRINK, POLYTETRAFLUOROETHYLENE TUBING STANDARD WALL (AWG Spaghetti sized tubing)

### **Applications**

PTFE0S is a standard wall non-shrink, flame retardant polytetrafluoroethylene tube. It is designed for a wide range of applications requiring high heat-resistance.

#### **Features**

- ★ Continuous operating temperature: -75 °C to +260 °C (-103 °F to +500 °F)
- ★ Highly heat-resistant
- ★ High resistance to chemicals and oils

#### **Standards**

- ★ Declared Dimension Life (DDL) 12 years
- ★ Meets V-0 Flammability
- ★ RoHS & REACH Compliant

### **Specification Values**

Property		Test Method	Value	
Physical	Specific Gravity (Max.)	ASTM D792	2.20	
	Elongation (Min.)	ASTM D638	200%	
	Tensile Strength (Min.)	ASTM D638	2500 psi	
	Hardness Durometer	ASTM D2240	D-60	
Electrical	Dielectric Strength	ASTM D149	1400 Volts/mil	
	Volume Resistivity (Min.)	ASTM D257	$10^{18}\Omega \cdot cm$	
General	Chemical/Solvent Resistance	-	Excellent	
	Water Absorption (Max.)	ASTM D570	0.01	
	Flammability Rating	UL 94	V-0	

Rev. March 2024





Fax: (469) 568-0808



## PTFE0S - Teflon®

# NON-SHRINK, POLYTETRAFLUOROETHYLENE TUBING STANDARD WALL (AWG Spaghetti sized tubing)



#### **Product Dimensions**

AWG Size	Inside Diameter						
	Internal Diameter in (D)		Internal Diameter mm (D)		Wall Thickness (Nominal) (t)		
	Min.	Max.	Min.	Max.	in	mm	
30	.010	.015	.254	.381	.009 ± .002	.229 ± .051	
28	.013	.018	.330	.480	.009 ± .002	.229 ± .051	
26	.016	.021	.410	.560	.009 ± .002	.229 ± .051	
24	.020	.026	.510	.670	.012 ± .003	.305 ± .076	
23	.023	.029	.584	.740	.012 ± .003	.305 ± .076	
22	.025	.032	.640	.810	.012 ± .003	.305 ± .076	
21	.029	.035	.740	.890	.012 ± .003	.305 ± .076	
20	.032	.040	.813	1.02	.016 ± .003	.406 ± .076	
19	.036	.044	.914	1.12	.016 ± .003	.406 ± .076	
18	.040	.049	1.02	1.25	.016 ± .003	.406 ± .076	
17	.045	.054	1.14	1.37	.016 ± .003	.406 ± .076	
16	.051	.061	1.30	1.55	.016 ± .003	.406 ± .076	
15	.057	.067	1.45	1.70	.016 ± .003	.406 ± .076	
14	.064	.074	1.63	1.88	.016 ± .003	.406 ± .076	
13	.072	.082	1.83	2.08	.016 ± .003	.406 ± .076	
12	.081	.091	2.06	2.31	.016 ± .003	.406 ± .076	
11	.091	.101	2.31	2.57	.016 ± .003	.406 ± .076	
10	.102	.112	2.59	2.85	.016 ± .003	.406 ± .076	
9	.114	.124	2.90	3.15	.020 ± .004	.508 ± .102	
8	.129	.141	3.28	3.58	.020 ± .004	.508 ± .102	
7	.144	.158	3.66	4.01	.020 ± .004	.508 ± .102	
6	.162	.178	4.11	4.52	.020 ± .004	.508 ± .102	
5	.182	.198	4.62	5.03	.020 ± .004	.508 ± .102	
4	.204	.224	5.18	5.69	.020 ± .004	.508 ± .102	
3	.229	.249	5.82	6.33	.020 ± .004	.508 ± .102	
2	.258	.278	6.55	7.06	.020 ± .004	.508 ± .102	
1	.289	.311	7.34	7.90	.020 ± .004	.508 ± .102	
0	.325	.347	8.26	8.81	.020 ± .004	.508 ± .102	

Rev. March 2024





Tel: (469) 568-0800 Fax: (469) 568-0808