

PTFE2L - Teflon®

2:1 SHRINK RATIO, POLYTETRAFLUOROETHYLENE TUBING LIGHT WALL

Applications

PTFE2L is a light wall, flame retardant heat shrinkable polytetrafluoroethylene tube. It is designed for a wide range of applications requiring high heat-resistance.

Features

- ★ Shrink ratio: 2:1 shrink ratio in the radial direction, ± 20% in the axial direction
- ★ Continuous operating temperature: -75 °C to +260 °C (-103 °F to +500 °F)
- ★ Highly heat-resistant
- ★ High resistance to chemicals and oils

Standards

- ★ Declared Dimension Life (DDL) 12 years
- ★ Meets V-0 Flammability
- ★ RoHS & REACH Compliant

Specification Values

Property		Test Method	Value	
Physical	Specific Gravity (Max.)	ASTM D792	2.20	
	Elongation (Min.)	ASTM D638	200%	
	Tensile Strength (Min.)	ASTM D638	2500 psi	
	Hardness Durometer	ASTM D2240	D-60	
Electrical	Dielectric Strength	ASTM D149	1400 Volts/mil	
	Volume Resistivity (Min.)	ASTM D257	$10^{18}\Omega\cdot cm$	
General	Chemical/Solvent Resistance	-	Excellent	
	Water Absorption (Max.)	ASTM D570	0.01	
	Flammability Rating	UL 94	V-0	

Rev. February 2024






Fax: (469) 568-0808



PTFE2L - Teflon®

2:1 SHRINK RATIO, POLYTETRAFLUOROETHYLENE TUBING LIGHT WALL



Fully recovered after heating

Product Dimensions

Minimum Shrink Temperature: 327 °C

rioduct L	71111611310	7113	willimum Shrink Temperature: 327 °C				
AWG Size	Expanded Internal Diameter (Minimum) (D)		Recovered				
			Internal Diameter (Maximum) (d)		Wall Thickness (Nominal) (t)		
	in	mm	in	mm	in	mm	
30	.034	.864	.015	.381	.006 ± .002	.152 ± .051	
28	.038	.965	.018	.457	.006 ± .002	.152 ± .051	
26	.046	1.17	.022	.559	.006 ± .002	.152 ± .051	
24	.050	1.27	.025	.644	.006 ± .002	.152 ± .051	
22	.055	1.40	.031	.790	.006 ± .002	.152 ± .051	
20	.060	1.53	.038	.970	.006 ± .002	.152 ± .051	
19	.065	1.65	.043	1.09	.006 ± .002	.152 ± .051	
18	.076	1.93	.046	1.17	.006 ± .002	.152 ± .051	
17	.085	2.16	.054	1.37	.006 ± .002	.152 ± .051	
16	.093	2.36	.057	1.45	.006 ± .002	.152 ± .051	
15	.110	2.79	.063	1.60	.006 ± .002	.152 ± .051	
14	.120	3.05	.072	1.83	.008 ± .002	.203 ± .051	
13	.140	3.56	.080	2.03	.008 ± .002	.203 ± .051	
12	.150	3.81	.089	2.26	.008 ± .002	.203 ± .051	
11	.170	4.32	.099	2.51	.008 ± .002	.203 ± .051	
10	.191	4.85	.110	2.79	.008 ± .002	.203 ± .051	
9	.205	5.21	.122	3.10	.008 ± .002	.203 ± .051	
8	.240	6.10	.139	3.53	.008 ± .002	.203 ± .051	
7	.270	6.86	.154	3.91	.008 ± .002	.203 ± .051	
6	.302	7.67	.172	4.37	.010 ± .003	.254 ± .076	
5	.320	8.13	.192	4.88	.010 ± .003	.254 ± .076	
4	.370	9.40	.214	5.44	.010 ± .003	.254 ± .076	
3	.390	9.91	.241	6.12	.010 ± .003	.254 ± .076	
2	.430	10.92	.270	6.86	.010 ± .003	.254 ± .076	
1	.450	11.43	.301	7.65	.010 ± .003	.254 ± .076	
0	.470	11.94	.347	8.81	.012 ± .003	.305 ± .076	

Rev. February 2024





Tel: (469) 568-0800 Fax: (469) 568-0808