

## PTFE2T - Teflon®

# 2:1 SHRINK RATIO, POLYTETRAFLUOROETHYLENE TUBING THIN WALL

### **Applications**

PTFE2T is a thin wall, flame retardant heat shrinkable polytetrafluoroethylene tube. It is designed for a wide range of applications requiring high heat-resistance.

#### **Features**

- ★ Shrink ratio: 2:1 shrink ratio in the radial direction, ± 20% in the axial direction
- ★ Continuous operating temperature: -75 °C to +260 °C (-103 °F to +500 °F)
- ★ Highly heat-resistant
- ★ High resistance to chemicals and oils

#### **Standards**

- ★ Declared Dimension Life (DDL) 12 years
- ★ Meets V-0 Flammability
- ★ RoHS & REACH Compliant

## **Specification Values**

	Property Test Method Value		Value	
	Specific Gravity (Max.)	ASTM D792	2.20	
Physical	Elongation (Min.)	ASTM D638	200%	
	Tensile Strength (Min.)	ASTM D638	2500 psi	
	Hardness Durometer	ASTM D2240	D-60	
Electrical	Dielectric Strength	ASTM D149	1400 Volts/mil	
Liectrical	Volume Resistivity (Min.)	ASTM D257	10 <sup>18</sup> Ω · cm	
	Chemical/Solvent Resistance	-	Excellent	
General	Water Absorption (Max.)	ASTM D570	0.01	
	Flammability Rating	UL 94	V-0	

Rev. February 2024






Fax: (469) 568-0808



## PTFE2T - Teflon®

# 2:1 SHRINK RATIO, POLYTETRAFLUOROETHYLENE TUBING THIN WALL



Fully recovered after heating

#### **Product Dimensions**

### Minimum Shrink Temperature: 327 °C

oduct Dimensions			Minimum Shrink Temperature: 327 °				
Size	Expanded  Internal Diameter (Minimum) (D)		Recovered				
			Internal Diameter (Maximum) (d)		Wall Thickness (Nominal) (t)		
AWG	in	mm	in	mm	in	mm	
30	.034	.864	.015	.381	.009 ± .002	.229 <b>±</b> .051	
28	.038	.965	.018	.457	.009 ± .002	.229 <b>±</b> .051	
26	.046	1.17	.022	.559	.010 ± .003	.254 <b>±</b> .076	
24	.050	1.27	.027	.686	.010 ± .003	.254 <b>±</b> .076	
22	.055	1.40	.032	.813	.012 ± .003	.305 ± .076	
20	.060	1.53	.039	.991	.012 ± .003	.305 ± .076	
19	.065	1.65	.043	1.09	.012 ± .003	.305 ± .076	
18	.076	1.93	.049	1.25	.012 ± .003	.305 ± .076	
17	.085	2.16	.054	1.37	.012 ± .003	.305 ± .076	
16	.093	2.36	.061	1.55	.012 ± .003	.305 <b>±</b> .076	
15	.110	2.79	.067	1.70	.012 ± .003	.305 <b>±</b> .076	
14	.120	3.05	.072	1.83	.012 ± .003	.305 <b>±</b> .076	
13	.140	3.56	.080	2.03	.012 ± .003	.305 ± .076	
12	.150	3.81	.089	2.26	.012 ± .003	.305 ± .076	
11	.170	4.32	.101	2.57	.012 ± .003	.305 ± .076	
10	.191	4.85	.112	2.85	.012 ± .003	.305 <b>±</b> .076	
9	.205	5.21	.124	3.15	.015 <b>±</b> .004	.381 <b>± .</b> 102	
8	.240	6.10	.141	3.58	.015 <b>±</b> .004	.381 <b>± .</b> 102	
7	.270	6.86	.158	4.01	.015 <b>±</b> .004	.381 <b>± .</b> 102	
6	.302	7.67	.178	4.52	.015 <b>±</b> .004	.381 <b>± .</b> 102	
5	.320	8.13	.198	5.03	.015 <b>±</b> .004	.381 <b>± .</b> 102	
4	.370	9.40	.224	5.69	.015 <b>±</b> .004	.381 <b>± .</b> 102	
3	.390	9.91	.249	6.32	.015 <b>±</b> .004	.381 <b>± .</b> 102	
2	.430	10.92	.278	7.06	.015 <b>±</b> .004	.381 <b>± .</b> 102	
1	.450	11.43	.311	7.90	.015 <b>±</b> .004	.381 <b>± .</b> 102	
0	.470	11.94	.347	8.81	.015 <b>±</b> .004	.381 <b>± .</b> 102	
Fractional							
1/8"	.215	5.46	.130	3.30	.015 <b>±</b> .003	.381 <b>±</b> .076	
1/4"	.410	10.41	.260	6.60	.015 <b>±</b> .004	.381 ± .102	
5/16"	.470	11.94	.329	8.36	.015 <b>±</b> .004	.381 ± .102	
3/8"	.560	14.22	.399	10.13	.015 <b>±</b> .003	.381 ± .076	
7/16"	.655	16.64	.462	11.73	.018 ± .004	.457 <b>±</b> .102	
1/2"	.750	19.05	.524	13.31	.018 ± .004	.457 <b>±</b> .102	
5/8"	.930	23.62	.655	16.64	.020 ± .004	.508 ± .102	
3/4"	1.125	28.58	.786	19.96	.025 ± .005	.635 ± .127	
7/8"	1.310	33.27	.911	23.14	.030 ± .006	.762 ± .152	
1"	1.500	38.10	1.036	26.31	.030 ± .006	.762 <b>±</b> .152	

Rev. February 2024





Tel: (469) 568-0800 Fax: (469) 568-0808