



DUNBAR – 1635S

2:1 SHRINK RATIO, SEMI-RIGID, FLAME RETARDANT, POLYOLEFIN TUBING

Applications

DUNBAR-1635S is designed for wire strain-relief applications and terminations, wire splices, soldered or crimped connections. It provides tough and high abrasion resistance for delicate components in mechanical environments.

Features

- ★ Shrink ratio: 50% or more in the radial direction, 5% or less in the axial direction
- ★ In stock for immediate shipments (Black, Clear, and Optional Colors)
- ★ Continuous operating temperature: - 55°C (-67°F) to 135°C (275°F)
- ★ Flammability: ASTM D2671 procedure B
- ★ High resistance to abrasion, chemicals and oils

Standard

- ★ AMS-DTL-23053/6 Class 1, Class 2 is Clear (Formerly MIL-DTL-23053/6 Class 1 & 2)
- ★ RoHS Compliant

Specification Values

Property		Test Method	Value	
Physical	Unaged	Tensile strength	Min. 2,000 psi	
		Elongation	Min. 200%	
	Aged	Elongation	Min. 100%	
	Fluid Resist.	Tensile strength	24°C/24 hrs	Min. 1,600 psi
		Dielectric strength	6 Fluids	Min. 400 Volts/mil
	Concentricity		ASTM D2671	Min. 70%
	Heat shock		250°C/4 hrs	No cracks, flowing or dripping
	Low temperature flexibility		- 55°C/4 hrs	No cracking
	Secant modulus		ASTM D882	Min. 25,000 psi
Specific gravity		ASTM D792	Max. 1.35 (Max. 1.00 Clear)	
Electrical	Dielectric strength		ASTM D2671	Min. 500 Volts/mil
	Volume resistivity		ASTM D876	Min. 10 ¹⁴ Ω - cm
Chemical	Copper corrosion		150°C/16 hrs	No corrosion
	Fungus resistance		ASTM G21	No growth
	Water Absorption		ASTM D570	Max. 0.5% (Max. 0.2% Clear)
	Flammability		ASTM D2671	Pass

Rev. May 2011



Dunbar Products, LLC


Your Stocking Partner for Quality Components

P.O Box 112218, Carrollton, TX, 75011-2218
 Tel: (469) 568-0800
 Fax: (469) 568-0808



DUNBAR – 1635S

2:1 SHRINK RATIO, SEMI-RIGID, FLAME RETARDANT, POLYOLEFIN TUBING



Fully recovered after heating

Product Dimensions

Minimum Shrink Temperature: 130°C

Size	Expanded		Recovered				Standard Spool Length
	Internal Diameter Minimum (D)		Internal Diameter Maximum (d)		Total Wall Thickness Minimum (t)		
	In.	mm	In.	mm	In.	mm	Ft.
3/64"	0.047	1.2	0.023	0.58	0.013	0.33	500
1/16"	0.063	1.6	0.031	0.79	0.014	0.36	500
3/32"	0.094	2.4	0.046	1.17	0.017	0.43	500
1/8"	0.126	3.2	0.062	1.57	0.017	0.43	500
3/16"	0.189	4.8	0.093	2.36	0.017	0.43	250
1/4"	0.252	6.4	0.125	3.18	0.022	0.56	250
3/8"	0.378	9.6	0.187	4.75	0.022	0.56	200
1/2"	0.500	12.7	0.250	6.35	0.022	0.56	200
3/4"	0.752	19.1	0.375	9.53	0.027	0.69	100
1"	1.0	25.4	0.5	12.70	0.030	0.76	100

Rev. May 2011



Dunbar Products, LLC

Your Stocking Partner for Quality Components

P.O Box 112218, Carrollton, TX, 75011-2218
 Tel: (469) 568-0800
 Fax: (469) 568-0808